



New Metals & Chemicals Ltd



PRODUCT INFORMATION

PVDF30

High Performance Foams

PVDF30 is a closed cell foams of density 30 kg/m³ made from polyvinyl fluoride which is available in sheet form. The material will thermoform into simple and complex shapes. The material offers excellent chemical resistance and flammability properties and meets BMS 8-371. This provisional data characterises the foam.

<u>PROPERTY</u>	<u>TEST METHOD</u>	<u>UNITS</u>	<u>TYPICAL VALUE</u>
<u>Density</u>	ISO 845	Kg m ⁻³	30
<u>Max. operating temperature</u>	Internal	°C	110
<u>Compression stress-strain Characteristics</u> 10% compression 25% compression 40% compression 50% compression	ISO 7214 (1 st compression)	kPa kPa kPa kPa	24 47 79 111
<u>Tensile strength</u> <u>Elongation</u>	ISO 1798 ISO 1798	KPa %	400 151
<u>Tear strength</u>	ISO 8067	N m ⁻¹	1015
<u>Compression set</u> (22 hrs @ 25% compression, 23°C, ½ hr recovery) (22 hrs @ 25% compression, 23°C 24 hrs recovery) (22 hrs @ 50% compression, 23°C, ½ hr recovery) (22 hrs @ 50% compression, 23°C, 24 hrs recovery)	ISO 7214 25mm cell-cell 25mm cell-cell ASTM D3575 25mm cell-cell 25mm cell-cell	 % set % set % set % set	 6 3 11.5 7.5
<u>Thermal conductivity</u> Mean temperature of 0°C Mean temperature of 40°C Mean temperature of 83°C	ISO 8301 DIN52 612 ASTM C 518	W m ⁻¹ k ⁻¹ W m ⁻¹ k ⁻¹ W m ⁻¹ k ⁻¹	0.033 0.038 0.046
<u>Flammability</u> Heat release Smoke density Smoke density Toxic gas emission Vertical bunsen burner Radiant panel	FAR/CS 25.853 (d) App F Pt IV FAR/CS 25.853 (d) App F Pt V ABD0031 para.7.3.2 ABD0031 para.7.3.2 FAR/CS 25.853 (a) App F Pt I (a), (1), (ii) FAR/CS 25.853 (a) App F Pt VI		Pass at 3 and 13mm Pass at 3 and 13mm Pass at 3 and 13mm Pass at 3 and 13mm Pass at 5 and 30mm Pass at 3 and 30mm

New Metals and Chemicals Ltd, Newmet House, Rue De St Lawrence, Waltham Abbey, Essex, EN9 1PF, UK
TEL INT 44 1992 711111 FAX INT 44 1992 768393 E Mail: materials@newmet.co.uk Web: www.newmet.co.uk

New Metals & Chemicals warrants that the products described and presented herein are of merchantable quality, but does not warrant their fitness for any particular use or make any other warranty, expressed or implied. Liability of New Metals and Chemicals under this warranty is limited to the replacement of its products found defective, or, at its option, a refund of the purchase price. The properties listed on this sheet are typical values, and are not intended for writing specifications. The technical information in this data sheet reflects the present state of our knowledge, but it is not to be interpreted as guaranteeing properties in products sold. Products are sold to many different specifications, and customers should clearly describe their requirements when requesting quotations, or placing orders.