



Product Data

HEMPEL'S THINNERS 08...

HEMPEL PAINT is produced and supplied in such a way that thinning is normally not necessary provided the paint is properly mixed/stirred.

However, if the paint is to be applied in a low film thickness (for instance as a "sealer coat") or if the paint has become too thick, e.g. in cold weather, the HEMPEL THINNER(s) indicated on the product data sheet may be added to obtain a consistency most suitable for application. As a general rule, thinning should be kept at a minimum as the quality of the paint work will suffer from too liberal thinning. However, if application is to take place at high temperatures (air and/or steel), thinning may even beyond the limits mentioned on the data sheets exceptionally be necessary in order to avoid dry-spray and poor film formation.

HEMPEL'S THINNERS are blended to give the best results with regard to brushability, spray properties, etc.

In some cases ordinary solvents may substitute. As such products are beyond our control, we disclaim any responsibility for the results.

In each case the respective product data sheet and - when available - the APPLICATION INSTRUCTIONS should be consulted. As regards the use of THINNERS for cleaning of tools, see REMARKS overleaf.

HEMPEL'S THINNER NO.	FLASH POINT	EXAMPLES OF GENERAL USE
08080	25°C/77°F	HEMPEL'S ANTIFOULINGS GLOBIC, OCEANIC and OLYMPIC HEMPALIN DECKPAINT 53240. HEMPAQUICK qualities All-purpose thinner for HEMPATEX qualities. HEMPATHANE topcoats and enamels.
08230	32°C/90°F	Thinner for HEMPALIN qualities (except HEMPALIN DECKPAINT 53240 and HEMPAQUICK qualities) and other alkyd-based products.
08450	23°C/73°F	General purpose thinner for HEMPADUR qualities.
08510	3°C/37°F HIGHLY FLAMMABLE	Special purpose thinner for HEMPATHANE ENAMEL 55100 HEMPATHANE TOPCOAT 55210
08570	4°C/39°F	HEMPEL'S SHOPPRIMER E 15280 HEMPEL'S SHOPPRIMER ZS 15722 HEMPEL'S SHOPPRIMER ZS 15890



HEMPEL'S THINNERS 08...

HEMPEL'S THINNER NO.	FLASH POINT	EXAMPLES OF GENERAL USE
08700	24°C/75°F	HEMPEL'S GALVOSILs For HEMPADURs used as "non-popping" sealers on GALVOSILs.

REMARKS: THINNER 08230 has a stronger thinning effect than white spirit or turpentine.

Tools can usually be cleaned with the THINNER prescribed for the product.

For cleaning of tools which have been used for HEMPADUR products, HEMPEL'S TOOL CLEANER 99610 is recommended. Do not use it for thinning, **nor for cleaning after use of polyurethane products, HEMPATHANEs.**

Note: **HEMPEL'S THINNERS are for professional use only.**

Safety: Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Material Safety Data Sheets and follow all local or national safety regulations. Avoid inhalation, avoid contact with skin and eyes, and do not swallow. Take precautions against possible risks of fire or explosions as well as protection of the environment. Apply only in well ventilated areas.

ISSUED BY: HEMPEL A/S

0808000000C0004
0823000000C0005
0845000000C0009
0851000000C0002
0857000000C0007
0870000000C0006

*This Product Data Sheet supersedes those previously issued.
For explanations, definitions and scope, see "Explanatory Notes" in the HEMPEL Book.
Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.
The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise.
Product data are subject to change without notice and become void five years from the date of issue.*