

PRODUCT NAME**Silicone Alkyd****HMG PAINTS LTD**

Collyhurst Road

Manchester, M40 7RU

Tel: 0161 205 7631 - Fax: 0161 205 8823

www.hmgpaint.com

sales@hmgpaint.com

Issue date 01/01/1998
Formula number 7040 series
Product code TOPSIL
Printed date Mon 26/11/01 at 11:49:53

PACKAGING

Available in 500ml, 1, 2½, 5 litre tins and 25 & 200 litre drums.

PRODUCT FUNCTION

HMG Silicone alkyd is a high quality synthetic enamel based on silicone modified resins, offering outstanding resistance to weathering combined with excellent colour & gloss retention.

HMG Silicon alkyd gives excellent adhesion and high heat stability whilst offering improved life and protection for general maintenance paint systems.

HMG Silicon alkyd is easy to use and can be applied over most conventional alkyd systems, enabling the product to be used to upgrade previously applied decorative and industrial coatings.

TECHNICAL INFORMATION

Solids Approximately 45 to 65% dependent on colour
Flashpoint Above 32°C
Specific Gravity 0.95 to 1.30 approximately dependent on colour
Viscosity 3 - 3.5 poise ICI Cone and Plate
Temp Resistance Up to 200°C for non-continuous heat situations
Storage 12 months in original sealed containers
Colour retention Excellent

APPLICATION AND USAGE DATA

Touch dry 1 hours
Firm dry 4 hours
Hard dry Overnight
Thinners HMG White Spirit or HMG Thinners 75
Overcoating overnight minimum
Eqp. cleaning HMG Gun cleaner
Film thickness 50 microns WFT gives approximately 25 microns DFT
Coverage 10 square metres per litre (theoretical)
VOC 520g/l

COLOUR RANGE

BS4800, BS2660, BS381C & RAL shades. Most other shades can be matched by arrangement in a range of sheens.

SPECIAL PROPERTIES

- High durability to weathering.
- Good heat resistance.

PREPARATION

Suitably primed surfaces must be thoroughly clean, dry, free, oil, grease or other contaminants.

Various HMG Undercoats and anti-corrosive primers are available.

For non-ferrous metals, HMG 2 Pack Etch Primer must be used.

For advice on any particular problem, please consult our Technical Department.

HOW TO USE

- Airless Brush Electrostatic HVLP
 Conventional spray Dipping Roller See application data

APPLICATION

Silicone alkyd enamel can be brushed or hot sprayed as supplied.

Technical Data Sheets are also available on our website at www.hmgpaint.com

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS. Such information is to the best of HMG's knowledge and belief accurate and reliable as of the date indicated. HOWEVER, NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE.

PRODUCT NAME**Silicone Alkyd****HMG PAINTS LTD**

Collyhurst Road

Manchester, M40 7RU

Tel: 0161 205 7631 - Fax: 0161 205 8823

www.hmgpaint.comsales@hmgpaint.com

Issue date	01/01/1998
Formula number	7040 series
Product code	TOPSIL
Printed date	Mon 26/11/01 at 11:49:53

For conventional air assisted spray use 10 -20% HMG Thinners 75.

HEALTH AND SAFETY

- Refer to health and safety data sheet and tin label prior to use.
- Wear suitable respiratory equipment when spraying.

Technical Data Sheets are also available on our website at www.hmgpaint.com

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS. Such information is to the best of HMG's knowledge and belief accurate and reliable as of the date indicated. HOWEVER, NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE.